

19



Europäisches Patentamt
European Patent Office
Office européen des brevets

11 Veröffentlichungsnummer:

11 Publication number:

11 Numéro de publication:

0 708 706

Internationale Anmeldung veröffentlicht durch die
Weltorganisation für geistiges Eigentum unter der Nummer:

WO 95/01868 (art.158 des EPf).

International application published by the World
Intellectual Property Organisation under number:

WO 95/01868 (art.158 of the EPC).

Demande internationale publiée par l'Organisation
Mondiale de la Propriété sous le numéro:


WO 95/01868 (art.158 de la CBE).

THIS PAGE BLANK (USPTO)

INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification ⁶ : B29C 70/48, B29D 31/00	A1	(11) International Publication Number: WO 95/01868 (43) International Publication Date: 19 January 1995 (19.01.95)
(21) International Application Number: PCT/GB94/01475 (22) International Filing Date: 7 July 1994 (07.07.94) (30) Priority Data: 9314311.3 10 July 1993 (10.07.93) GB (71) Applicant (for all designated States except US): 3-D COMPOS- ITES LIMITED [GB/GB]; Brackenthwaite House, Black Beck Wood, Storrs Park, Bowness, Cumbria LA23 3LS (GB). (72) Inventor; and (75) Inventor/Applicant (for US only): NEWTON, John, Reginald [GB/GB]; Brackenthwaite House, Black Beck Wood, Storrs Park, Bowness, Cumbria LA23 3LS (GB). (74) Agent: WHARTON, Peter, Robert; Urquhart-Dykes & Lord, Inventions House, Valley Court, Canal Road, Bradford BD1 4SP (GB).		(81) Designated States: CA, JP, US, European patent (AT, BE, CH, DE, DK, ES, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE). Published <i>With international search report.</i>

(54) Title: COMPOSITE ARTICLE AND METHOD FOR MANUFACTURING THE SAME



(57) Abstract

A method of moulding a composite article by injecting a plastics material resin into fibres within a mould is characterised in that a continuous web of fibres (10) is laid in a mould in such a fashion that a honeycomb structure is produced without the web crossing itself. In a preferred form of the method the honeycomb is laminated to a plate (17) during moulding by providing a flat sheet of fibres contiguous with the honeycomb structure and injecting the whole simultaneously. If desired, a honeycomb structure can be provided on either side of the plate. A continuous web (10) of mainly longitudinal fibres (12) is used for the web to give the composite load bearing strength.

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AT	Austria	GB	United Kingdom	MR	Mauritania
AU	Australia	GE	Georgia	MW	Malawi
BB	Barbados	GN	Guinea	NE	Niger
BE	Belgium	GR	Greece	NL	Netherlands
BF	Burkina Faso	HU	Hungary	NO	Norway
BG	Bulgaria	IE	Ireland	NZ	New Zealand
BJ	Benin	IT	Italy	PL	Poland
BR	Brazil	JP	Japan	PT	Portugal
BY	Belarus	KE	Kenya	RO	Romania
CA	Canada	KG	Kyrgyzstan	RU	Russian Federation
CF	Central African Republic	KP	Democratic People's Republic of Korea	SD	Sudan
CG	Congo	KR	Republic of Korea	SE	Sweden
CH	Switzerland	KZ	Kazakhstan	SI	Slovenia
CI	Côte d'Ivoire	LI	Liechtenstein	SK	Slovakia
CM	Cameroon	LK	Sri Lanka	SN	Senegal
CN	China	LU	Luxembourg	TD	Chad
CS	Czechoslovakia	LV	Latvia	TG	Togo
CZ	Czech Republic	MC	Monaco	TJ	Tajikistan
DE	Germany	MD	Republic of Moldova	TT	Trinidad and Tobago
DK	Denmark	MG	Madagascar	UA	Ukraine
ES	Spain	ML	Mali	US	United States of America
FI	Finland	MN	Mongolia	UZ	Uzbekistan
FR	France			VN	Viet Nam
GA	Gabon				

-1-

COMPOSITE ARTICLE AND METHOD FOR MANUFACTURING THE SAME

This invention relates to a composite article and a method of moulding composite articles from fibre reinforced synthetic curable resins.

The composite access covers described in our European patent number 0147050 have an internal structure which is very efficient and leads to high load bearing qualities for the weight of material used. The design of this structure is based on the concept of employing two plates which are separated by webs. A structure of this type provides a high value of second moment of area, in relation to the quantity of material used, and the greater this value the stiffer the structure will be and the greater its load bearing capacity. Within the structure the reinforcing fibres are arranged in an optimised manner. That is, the fibres are arranged so as to correspond with the direction of the anticipated stresses which will occur within the structure when subjected to load.

Our European patent numbers 0365579 and 0408639 describe methods which enable the complex three dimensional structure of these access covers to be injected with a matrix resin in a very effective and speedy manner even when high fibre volume fractions are employed. In order to obtain the necessary strength to weight ratio in load bearing composite articles of this type, it is necessary to employ very high fibre volume fractions. The access covers referred to above have fibre volume fractions ranging from 43-50%. Normally such high fibre volume fractions are very difficult to inject in commercially acceptable moulding times, which limited the size of composite article which could be moulded prior to the process of our above mentioned European patents.

Access covers and other load bearing composite articles made as described above are excellent high load bearing structures

-2-

capable of competing with the hitherto used alternatives fabricated from metal. However, when the load requirements are less severe, for example an access cover for pedestrian areas, it is desirable to reduce the cost of production. A significant proportion of the expense in the structures referred to above is contributed by the polyurethane foam cores used to create the three dimensional structure. It would therefore be an advantage, in respect of medium duty structures, to eliminate the polyurethane cores while still retaining the structural benefits of a high fibre volume fraction.

The invention seeks to provide a composite article, and method of making the same, improved in the above respects.

According to the present invention there is provided a method of moulding a composite article by injecting a plastics material resin into fibres within a mould characterised in that a continuous web of fibres is laid in a mould in such a fashion that a honeycomb structure is produced without the web crossing itself.

The term "honeycomb" is used herein to refer to spaces being enclosed by the web where it touches itself but should not be construed as being limited to such spaces being hexagonal or even being regular in nature.

The invention extends to a composite article produced by the method described above.

In a preferred form of the method of the invention the honeycomb is laminated to a plate during moulding by providing a flat sheet of fibres contiguous with the honeycomb structure and injecting the whole simultaneously. If desired, a honeycomb structure can be provided on either side of the plate. Alternatively, if required, a plate may be provided on either side of the honeycomb structure but in this case it is

-3-

necessary to use foam inserts to prevent seepage of the resin into the interstices of the honeycomb and in this case the cost advantage over the structure described in European patent number 0 147 050 is not as great. Nevertheless there are certain circumstances in which such a structure is desirable and it remains within the ambit of the present invention.

The fibrous web forming the honeycomb is, as referred to above, preferably continuous throughout the article being moulded. Discontinuities in the web lead to weak spots in the moulded structure. In order for the web to be continuous, the way in which it is placed in the mould needs to be thought out carefully as described more fully hereinafter. The web may contain substantially parallel fibres (in its longitudinal direction) or may, preferably, be a laminate of mainly longitudinal fibres with some fibres arranged at an angle to the longitudinal direction in order to cater for the direction of stress likely to be found in the finished composite. A particularly preferred construction comprises 70% of longitudinal fibres together with 15% of fibres arranged at +45° to the longitudinal direction and 15% of fibres arranged at -45° to the longitudinal direction. Other configurations are of course possible.

The composite article of the invention may be used as a simple grating or, when integral with a sheet, may be used as a structural component, e.g. a floor panel, where medium to high load bearing is required (but not the very high load bearing capacity needed by access covers e.g. the ability to bear the weight of a petrol tanker). With the preferred embodiments of the invention not requiring the use of polyurethane foam core inserts, the composite article of the invention can be produced more cheaply for these medium to high load bearing requirements.

The invention will be described further, by way of example, with reference to the accompanying drawings, in which:

-4-

Figure 1 is a partial perspective view of a fibrous web for use in the method and article of the invention;

Figure 2 is a partial perspective view of the web in the form of a honeycomb; and

Figure 3 is a plan view of the web showing the direction in which it is laid in order to build up the honeycomb.

Referring to the drawings, the first stage in the production of a composite article in accordance with the invention is to produce a tape of structural fibres which will form the web 10. The tape is preferably formed from continuous fibres, the majority being crimp free, and the fibres are arranged in a configuration commensurate with providing the required strength properties for the reinforcing web. In figure 1 a web 10 is shown in which the majority (70%) of the fibres 12 are arranged substantially longitudinally of the web 10. 15% of the fibres 14 are arranged at an angle of -45° to the longitudinal direction and a further 15% of the fibres 16 are arranged at an angle of $+45^\circ$ to the longitudinal direction. The tape is held together by stitching using, for example, a polyester thread. The 45° fibres 14,16 specifically provide resistance to shear forces within the web while the longitudinal fibres 12 provide strength along the length of the web. The density of fibres in the web is arranged so as to provide a high fibre volume fraction, which is designed to match that of the plate portion of the laminate (if used) thus ensuring balanced mechanical properties and consistent flow properties during injection of the matrix resin.

The web 10 is laid into one half of a mould having indentations in the desired honeycomb pattern (not shown) in a manner that produces the desired configuration while avoiding the need for any discontinuity of the web structure or any crossing over of the web.

-5-

Referring to figure 3, this is achieved as follows. Starting at point 1 the tape is laid into the mould by advancing to points 2, 3, 4 and then 5. The arrows in figure 3 indicate the path of the web. This pattern is repeated until the complete honeycomb has been laid, at which point the tape is cut.

If the composite article is to include an integrally laminated plate 17 (Figure 2), a flat fibre sheet which will form the top (or bottom) plate of the structure is laid into the mould on top of the web 10. The fibres at the edges of the web are in direct contact with the fibres of the plate laminate and are compressed by closure of the mould to the same fibre volume fraction. The fibres within the plate laminate, like the web, would also be arranged to distribute and support the load according to the end use of the particular structure.

The mould having been closed, the structure is then injected with a matrix resin to form a one-piece composite article. Preferably, injection would be by one of the methods of network injection moulding referred to in our above mentioned European patents thus achieving high flow rates during the injection cycle and the potential for rapid cure and hence short cycle times. As described in those patents, a number of matrix resins can be employed but polyester resins are usually preferred.

An example of the injection system is as follows. Referring to figure 2, resin is injected into a port 18 in the mould from where it is distributed across the composite via a gallery 20 in the mould. It also is simultaneously distributed down galleries 22 in the web structure to a lower gallery 24 in the bottom mould half. In this way, the resin is injected rapidly across the width of the mould at both the top and bottom of the web 10. From there the resin diffuses through the web 10 to either side until it has completely wetted the entire web 10 leaving no dry spots. After this, injection

-6-

is halted and the resin cured, allowing the article then to be de-moulded. The galleries 20 and 24 in the mould should be in accordance with our European patent number 0408639 in that they should be of such a size and orientation that no substantial deformation of the fibres into the galleries occurs. One way of achieving this is to have a bridge piece in the upper mould half which pushes the glass fibres down and leaves a void forming the required gallery.

As mentioned above the composite article can be varied in various ways. For example a web could be provided on both sides of the plate 17, or the web could be made as a component in its own right and would make an excellent grating. The tape forming the web 10 could be woven as a honeycomb structure, rather than laid up as such a structure, although the final fibre architecture would remain as described above. The web 10 could be assembled between two plates by incorporating polyurethane foam inserts to form a structure comparable with the access cover of our above mentioned European patent number 0147050. The cost advantage in this case is less but it may nevertheless be useful for certain end uses. Naturally the composite article of the invention can be incorporated into and be part of a larger structure.

The fibres used will be fibres conventionally employed to produce structural composite articles and may include, without limitation, glass, Kevlar, carbon and the like.

The invention provides a method and article having an excellent load bearing configuration. Moreover, using an orientated continuous fibre architecture with a high value of fibre volume fraction (typically greater than 40%), leads to high load bearing capabilities. Additionally, especially if one of our above mentioned network injection moulding processes is employed, the manufacture is very efficient and even large structures can be produced within commercially acceptable moulding times

-7-

CLAIMS

1. A method of moulding a composite article by injecting a plastics material resin into fibres within a mould characterised in that a continuous web of fibres is laid in a mould in such a fashion that a honeycomb structure is produced without the web crossing itself.

2. A method as claimed in claim 2 in which the honeycomb is laminated to a plate during moulding by providing a flat sheet of fibres contiguous with the honeycomb structure and injecting the whole simultaneously.

3. A method as claimed in claim 2 in which a honeycomb structure is provided on either side of the plate.

4. A method as claimed in any of claims 1 to 3 in which the fibrous web forming the honeycomb is continuous throughout the article being moulded.

4. A method as claimed in any of claims 1 to 3 in which the web contains substantially parallel fibres in its longitudinal direction

5. A method as claimed in any of claims 1 to 3 in which the web is a laminate of mainly longitudinal fibres with some fibres arranged at a angle to the longitudinal direction in order to cater for the direction of stress likely to be found in the finished composite.



6. A method as claimed in claim 5 in which the web comprises 70% of longitudinal fibres together with 15% of fibres arranged at +45° to the longitudinal direction and 15% of fibres arranged at -45° to the longitudinal direction.

-8-

7. A composite article produced by a method as claimed in any of claims 1 to 6.

8. An article as claimed in claim 7 used as a simple grating.

9. An article as claimed in claim 7 having an integral sheet and used as a structural component, e.g. a floor panel.



2/2




Fig. 3.

INTERNATIONAL SEARCH REPORT

Int. Application No

PC 94/01475

A. CLASSIFICATION OF SUBJECT MATTER
IPC 6 B29C70/48 B29D31/00

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)
IPC 6 B29C B29D

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	GB,A,2 189 425 (CAMBRIAN PLASTICS LTD) 28 October 1987 see page 1, line 88 - line 101; figure 1 ---	1,7
A	FR,A,2 376 739 (A. DUBOIS) 4 August 1978 see page 4, line 10 - line 33; figure 6 ---	1,7
A	US,A,3 391 038 (G. W. WHITESIDES) 2 July 1968 see column 4, line 60 - column 5, line 14; figures 1,3 see column 6, line 1 - line 14 ---	1,7
A	US,A,4 137 354 (J. T. MAYES JR. ET AL.) 30 January 1979 see the whole document ---	1,7
-/--		

☒ Further documents are listed in the continuation of box C.☒ Patent family members are listed in annex.

* Special categories of cited documents :

- *A* document defining the general state of the art which is not considered to be of particular relevance
- *E* earlier document but published on or after the international filing date
- *L* document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- *O* document referring to an oral disclosure, use, exhibition or other means
- *P* document published prior to the international filing date but later than the priority date claimed

- *T* later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention
- *X* document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone
- *Y* document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.
- *&* document member of the same patent family

Date of the actual completion of the international search

13 October 1994

Date of mailing of the international search report

03 -11- 1994

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+ 31-70) 340-2040, Tx. 31 651 epo nl,
Fax: (+ 31-70) 340-3016

Authorized officer

Fregosi, A

INTERNATIONAL SEARCH REPORT

Int. l. Application No

PCT/GB 94/01475

C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	WO,A,89 09686 (3-D COMPOSITES LTD) 19 October 1989 cited in the application see the whole document ---	1,7
A	WO,A,89 00495 (3-D COMPOSITES LTD.) 26 January 1989 cited in the application see the whole document -----	1,7

INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No

PCT/94/01475

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
GB-A-2189425	28-10-87	NONE	
FR-A-2376739	04-08-78	NONE	
US-A-3391038		NONE	
US-A-4137354	30-01-79	NONE	
WO-A-8909686	19-10-89	DE-T- 68907594 EP-A, B 0408639 JP-T- 3504475 US-A- 5236321	21-10-93 23-01-91 03-10-91 17-08-93
WO-A-8900495	26-01-89	AU-B- 609163 AU-A- 1987988 CA-A- 1326117 CN-A- 1031046 DE-A- 3879704 DE-T- 3879704 EP-A, B 0365579 JP-T- 3503866 US-A- 5132069	26-04-91 13-02-89 18-01-94 15-02-89 29-04-93 14-10-93 02-05-90 29-08-91 21-07-92

THIS PAGE BLANK (USPTO)